



## TECHNICAL DATASHEET

# ***NISTRIP 1470***

## **NICKEL STRIPPING PROCESS**

NISTRIP 1470 is designed for easily stripping nickel coated pieces. Does not attack to the base metal.

### **Application:**

<b>NISTRIP 1470 A</b>	75-100 g/l
<b>NISTRIP 1471 B</b>	15-25 ml/l
<b>Temperature</b>	75-90 C
<b>Immersion time</b>	changes to thickness of the deposit

### **Make up data:**

1. Dissolve required amount of NISTRIP 1470 A in hot water ( Attention: wear protective equipment, gloves, eyeglasses,etc..)
2. Add required amount of NISTRIP 1471 B and stir.
3. Heat the solution to required degree.

Solution is ready for working

### **Effluent treatment:**

All concentrates and rinsing waters have to be treated according to local regulations.

## **Health and Safety**

Material Safety Data Sheets are available for all GALVANO MONDO products, they are normally issued with relevant quotations and Technical Data Sheets. They explain hazards associated with the product following classification by European Statutory Requirements. Normally more than one product will be used in a process. Risk evaluation of the process is the users responsibility because the user controls men, materials, methods and machines. The user must consider all of the substances present in the solution, whether they present a risk to people and the environment, whether abatement measures are needed.